

Table of Various Standards of Silicon Steels (CRGO)

Japan(NSC)	U.S.A. (AISI)	German(ORSI)	U.K.(BS601 .P.2)
	M-3 0.23mm	ORSI080	
23Z110	M-2 0.23mm		
	M-1 0.23mm	ORSIH103	
23ZH100	M-0H 0.23mm	ORSIH099	
23ZH95		ORSIH095	
23ZH90		ORSIH90L	
		ORSIH089	27M4
27Z130	M-4 0.27mm	ORSIH083	27M3
27Z120	M-3 0.27mm		
27ZH110	M-1H 0.27mm		
27ZH100	M-0H 0.27mm	ORSIH103	
27ZH95		ORSIH097	
27ZDKH95		ORSIH095L	
		ORSI097	30M5
30Z140	M-5 0.30mm	ORSI091	
30Z130	M-4 0.30mm		
30Z120	M-2H 0.30mm	ORSIH117	30M2H
30ZH120			
30ZH110	M-1H 0.30mm	ORSIH111	30M1H
30ZH105	M-0H 0.30mm	ORSIH105	
30ZH100		ORSIH100	
		ORSI111	35M6
35Z155	M-6 0.35mm	ORSI100	
35Z145	M-5 0.35mm		
35Z135			
35ZH135			
	M-3H 0.35mm		35M3H
35ZH125	M-2H 0.35mm		
35ZH115	M-1H 0.35mm		